

# Visão Geral Sylomer®

by getzner  
**sylomer®**

## Material

Poliuretano de células mistas (PUR) com propriedades amortecedoras e elásticas combinadas.

## Especificação dos padrões de entrega

Espessura: 12,5 mm / 25 mm

Rolos: 1,5 m de largura, 5,0 m comprimento

Tiras: até 1,5 m de largura, até 5,0 m comprimento

Componentes estampados com outras dimensões e componentes moldados estão disponíveis mediante pedido.

## Sylomer® Tipo de material



Propriedades	Procedimentos de teste	SR 11	SR 18	SR 28	SR 42	SR 55	SR 110	SR 220	SR 450	SR 850	SR 1200
Cor		amarelo	laranja	azul	rosa	verde	marrom	vermelho	cinza	turquesa	violeta
Faixa estática de uso <sup>1</sup> em N/mm <sup>2</sup>		0,011	0,018	0,028	0,042	0,055	0,110	0,220	0,450	0,850	1,200
Picos de carga <sup>1</sup> em N/mm <sup>2</sup>		0,50	0,75	1,00	2,00	2,00	3,00	4,00	5,00	6,00	6,00
Fator de perda mecânica	DIN 53513 <sup>2</sup>	0,25	0,23	0,21	0,18	0,17	0,14	0,13	0,12	0,11	0,11
Recuperação elástica em %	EN ISO 8307	45	45	50	50	55	55	55	60	60	60
Deformação residual por compressão <sup>3</sup> em %	EN ISO 1856	<5	<5	<5	<5	<5	<5	<5	<5	<5	<5
Módulo de elasticidade estático <sup>1</sup> em N/mm <sup>2</sup>		0,06	0,10	0,17	0,28	0,37	0,87	1,44	3,30	7,20	10,40
Módulo de elasticidade estático <sup>1</sup> em N/mm <sup>2</sup>	DIN 53513 <sup>2</sup>	0,17	0,28	0,44	0,61	0,75	1,36	2,54	5,04	11,10	16,40
Módulo de cisalhamento estático <sup>1</sup> em N/mm <sup>2</sup>	DIN ISO 1827 <sup>2</sup>	0,04	0,05	0,07	0,11	0,13	0,23	0,35	0,58	0,80	0,90
Módulo de cisalhamento dinâmico <sup>1</sup> em N/mm <sup>2</sup>	DIN ISO 1827 <sup>2</sup>	0,10	0,12	0,15	0,21	0,26	0,42	0,64	1,00	1,40	1,60
Tensão mínima de ruptura à tração em N/mm <sup>2</sup>	DIN EN ISO 527-3/5/100 <sup>2</sup>	0,30	0,35	0,40	0,50	0,60	0,80	1,20	1,80	2,50	2,70
Tensão mínima de ruptura ao alongamento em %	DIN EN ISO 527-3/5/100 <sup>2</sup>	300	300	250	250	250	220	200	170	170	160
Abrasão <sup>3</sup> em mm <sup>3</sup>	DIN EN ISO 4649	1.400	700	1.300	1.200	1.100	1.100	1.000	400	300	350
Coeficiente de atrito (aço)	Getzner Werkstoffe	≥0,5	≥0,5	≥0,5	≥0,5	≥0,5	≥0,5	≥0,5	≥0,5	≥0,5	≥0,5
Coeficiente de atrito (concreto)	Getzner Werkstoffe	≥0,7	≥0,7	≥0,7	≥0,7	≥0,7	≥0,7	≥0,7	≥0,7	≥0,7	≥0,7
Resistividade específica em Ω·cm	DIN IEC 60093	>10 <sup>12</sup>	>10 <sup>11</sup>	>10 <sup>11</sup>	>10 <sup>11</sup>	>10 <sup>11</sup>	>10 <sup>11</sup>	>10 <sup>11</sup>	>10 <sup>11</sup>	>10 <sup>10</sup>	>10 <sup>10</sup>
Condutividade térmica em W/mK	DIN EN 12667	0,045	0,050	0,050	0,055	0,060	0,075	0,090	0,110	0,130	0,140
Temperatura operacional em °C		-30 a 70									
Pico de temperatura em °C	curto prazo <sup>4</sup>	120									
Flamabilidade	EN ISO 11925-2	Classe E/EN 13501-1									

<sup>1</sup> Dados válidos para o fator de forma de q = 3

<sup>2</sup> Procedimento de medida semelhante ao padrão relevante

<sup>3</sup> A medição da abrasão depende da densidade com parâmetros de teste variáveis

<sup>4</sup> Dependendo da aplicação

Todas as informações e dados são baseados no nosso conhecimento atual. Os dados podem ser aplicados para cálculos e, como diretriz, estão sujeitos a tolerâncias típicas de fabricação, e não são garantidos. Reservamo-nos o direito de retificar os dados.

As folhas de dados sobre os diversos tipos de material e especificações detalhadas estão disponíveis mediante pedido.

# Overview Sylomer®



## Material

Mixed cellular PU elastomer (Polyurethane) with combined spring and dampening properties.

## Standard delivery specifications

Thickness: 12.5 mm / 25 mm

Rolls: 1.5 m wide, 5.0 m long

Strips: up to 1.5 m wide, up to 5.0 m long

Other dimensions, punched and moulded parts on request.

## Sylomer® Material type



Properties	Test procedures	SR 11	SR 18	SR 28	SR 42	SR 55	SR 110	SR 220	SR 450	SR 850	SR 1200
Color		yellow	orange	blue	pink	green	brown	red	grey	turquoise	violet
Static range of use <sup>1</sup> in N/mm <sup>2</sup>		0.011	0.018	0.028	0.042	0.055	0.110	0.220	0.450	0.850	1.200
Load peaks <sup>1</sup> in N/mm <sup>2</sup>		0.50	0.75	1.00	2.00	2.00	3.00	4.00	5.00	6.00	6.00
Mechanical loss factor	DIN 53513 <sup>2</sup>	0.25	0.23	0.21	0.18	0.17	0.14	0.13	0.12	0.11	0.11
Rebound elasticity in %	EN ISO 8307	45	45	50	50	55	55	55	60	60	60
Compression <sup>3</sup> set in %	EN ISO 1856	<5	<5	<5	<5	<5	<5	<5	<5	<5	<5
Static modulus of elasticity <sup>1</sup> in N/mm <sup>2</sup>		0.06	0.10	0.17	0.28	0.37	0.87	1.44	3.30	7.20	10.40
Dynamic modulus of elasticity <sup>1</sup> in N/mm <sup>2</sup>	DIN 53513 <sup>2</sup>	0.17	0.28	0.44	0.61	0.75	1.36	2.54	5.04	11.10	16.40
Static shear modulus <sup>1</sup> in N/mm <sup>2</sup>	DIN ISO 1827 <sup>2</sup>	0.04	0.05	0.07	0.11	0.13	0.23	0.35	0.58	0.80	0.90
Dynamic shear modulus <sup>1</sup> in N/mm <sup>2</sup>	DIN ISO 1827 <sup>2</sup>	0.10	0.12	0.15	0.21	0.26	0.42	0.64	1.00	1.40	1.60
Min. tensile stress at rupture in N/mm <sup>2</sup>	DIN EN ISO 527-3/5/100 <sup>2</sup>	0.30	0.35	0.40	0.50	0.60	0.80	1.20	1.80	2.50	2.70
Min. tensile elongation at rupture in %	DIN EN ISO 527-3/5/100 <sup>2</sup>	300	300	250	250	250	220	200	170	170	160
Abrasion <sup>3</sup> in mm <sup>3</sup>	DIN EN ISO 4649	1,400	700	1,300	1,200	1,100	1,100	1,000	400	300	350
Coefficient of friction (steel)	Getzner Werkstoffe	≥ 0.5	≥ 0.5	≥ 0.5	≥ 0.5	≥ 0.5	≥ 0.5	≥ 0.5	≥ 0.5	≥ 0.5	≥ 0.5
Coefficient of friction (concrete)	Getzner Werkstoffe	≥ 0.7	≥ 0.7	≥ 0.7	≥ 0.7	≥ 0.7	≥ 0.7	≥ 0.7	≥ 0.7	≥ 0.7	≥ 0.7
Specific volume resistance in Ω·cm	DIN IEC 60093	>10 <sup>12</sup>	>10 <sup>11</sup>	>10 <sup>11</sup>	>10 <sup>11</sup>	>10 <sup>11</sup>	>10 <sup>11</sup>	>10 <sup>11</sup>	>10 <sup>11</sup>	>10 <sup>10</sup>	>10 <sup>10</sup>
Thermal conductivity in W/mK	DIN EN 12667	0.045	0.050	0.050	0.055	0.060	0.075	0.090	0.110	0.130	0.140
Operating temperature in °C		-30 to 70									
Temperature peak in °C	short term <sup>4</sup>	120									
Flammability	EN ISO 11925-2	class E/EN 13501-1									

<sup>1</sup> Data valid for a form factor of q=3

<sup>2</sup> Tests according to respective standards

<sup>3</sup> Testing parameters vary depending on density

<sup>4</sup> Application-specific

All information and data is based on our current knowledge. The data can be applied for calculations and as guidelines, are subject to typical manufacturing tolerances, and are not guaranteed. We reserve the right to amend the data.

Data sheets on the various material types and special specifications available on request.

