SYLODYN® NC

NC

DATA SHEET

Product characteristics

Material	closed-cell PU elastomer (polyurethane)
Colour	yellow
Standard delivery dimension	Thickness: 12.5 mm / 25 mm
	Roll: 1.5 m wide, 5.0 m long
	Strip: up to 1.5 m wide, up to 5.0 m long

Other dimensions, punched and molded parts on request.

Range of use	**Compressive load**	**Deformation**
	shape factor-dependent, values apply to shape factor 3	
Static range of use (static loads)	up to 0.15 N/mm²	approx. 10 %
Dynamic range of use (static plus dynamic loads)	up to 0.25 N/mm²	approx. 21 %
Load peaks (occasional, brief loads)	up to 3.0 N/mm²	approx. 60 %

Standard Sylodyn® range

Static range of use



Material properties		**Test methods**	**Comment**
Mechanical loss factor	0.07	ISO 4664-1[1]	temperature-, frequency-, specific load- and amplitude-dependent
Rebound resilience	70 %	EN ISO 8307[1]	
Compression hardness[3]	0.15 N/mm²	EN ISO 844[1]	at 10 % linear compression, 3rd load cycle
Compression set[2]	< 5 %	EN ISO 1856[1]	50 % deformation, 23 °C, 72 h, 30 min after removal of load
Static modulus of elasticity[3]	1.13 N/mm²		at specific load of 0.15 N/mm²
Dynamic modulus of elasticity[3]	1.32 N/mm²	ISO 4664-1[1]	at specific load of 0.15 N/mm², 10 Hz
Static shear modulus	0.19 N/mm²	DIN ISO 1827[1]	at a pretension of 0.15 N/mm²
Dynamic shear modulus	0.26 N/mm²	DIN ISO 1827[1]	at a pretension of 0.15 N/mm², 10 Hz
Min. tensile stress at rupture	1.40 N/mm²	EN ISO 527-3/5/500[1]	
Min. tensile elongation at rupture	300 %	EN ISO 527-3/5/500[1]	
Abrasion[2]	≤ 300 mm³	DIN ISO 4649[1]	load 5 N
Coefficient of friction (steel)	0.7	EN ISO 8295[1]	dry, static friction
Coefficient of friction (concrete)	0.7	EN ISO 8295[1]	dry, static friction
Coefficient of friction (wood)	0.5	EN ISO 8295[1]	dry, static friction
Specific volume resistance	$>10^{10}$ Ω·cm	EN IEC 62631-3-1[1]	dry
Thermal conductivity	0.08 W/(mK)	EN 12667	
Temperature range	-30 °C to 70 °C		short term higher temperatures possible
Flammability	class E	EN ISO 11925-2	normal combustible, EN 13501-1

[1] Measurement / evaluation in accordance with the relevant standard
[2] The measurement is performed on a density-dependent basis with differing test parameters
[3] Values apply to shape factor 3

getzner

Load deflection curve



Fig. 1: Quasi-static load deflection curve for different bearing thicknesses

Quasi-static load deflection curve measured with a loading rate of 0.015 N/mm²/s.

Testing between flat and plane-parallel steel plates, recording of 3rd load, with filtered starting range in accordance with ISO 844, testing at room temperature.

Parameter: thickness of the Sylodyn® bearing

Shape factor 3

Modulus of elasticity



Fig. 2: Load dependency of the static and dynamic modulus of elasticity

Quasi-static modulus of elasticity as tangential modulus from the load deflection curve. Dynamic modulus of elasticity from sinusoidal excitation with a velocity level of 100 dB_v re. $5 \cdot 10^{-8}$ m/s corresponding to a vibration amplitude of 0.22 mm at 10 Hz and 0.08 mm at 30 Hz.

Measurement in accordance with ISO 4664-1

Parameter: frequency

Shape factor 3

by getzner sylodyn®

Natural frequencies



Fig. 3: Natural frequencies for different bearing thicknesses

Natural frequencies of a vibratory system with a single degree of freedome, consisting of a mass and an elastic bearing made of Sylodyn® NC on a rigid surface.

Parameter: thickness of the Sylodyn® bearing

Shape factor 3

Vibration isolation efficiency



Fig. 4: Factor of transmission and isolation rate

Reduction of the transmitted mechanical vibrations by implementation of an elastic bearing consisting of Sylodyn® NC based on a stiff subgrade.

Parameter: factor of transmission in dB, isolation rate in %

by getzner sylodyn®

Influence of the shape factor

The graphs show the material properties at different shape factors.



Fig. 5: Static range of use in relation to the shape factor



Fig. 6: Deflection[4] at constant thickness in relation to the shape factor



Fig. 7: Dynamic modulus of elasticity[4] at 10 Hz in relation to the shape factor



Fig. 8: Natural frequency[4] at constant thickness in relation to the shape factor

[4] Reference values: specific load 0.15 N/mm², shape factor 3

Material properties can be determined using the online calculation program FreqCalc. The program can be accessed via www.getzner.com (registration necessary).

All information and data is based on our current knowledge. The data can be applied for calculations and as guidelines, are subject to typical manufacturing tolerances and are not guaranteed. Material properties as well as their tolerances can vary depending on type of application or use and are available from Getzner on request.

Further information can be found in VDI Guideline 2062 (Association of German Engineers) as well as in glossary. Further characteristic values on request.

Our printing is **climate neutral.**

Data sheet Sylodyn NC EN © Copyright by Getzner Werkstoffe GmbH
08-2026 | Subject to change without notice.

WMUF.AT